SAFETY DATA SHEETS

This SDS packet was issued with item: 076362263

N/A

"Reviewed September 2010: No Changes"

laterial Safety Data Sheet ay be used to comply with	U.S. Departm	ent of Lebor	lls	Section V -	Reactivity Dat	le ,		••••••••••••••••••••••••••••••••••••••
SHA's Hazard Communication Standard.	- Occupational Safe (Non-Mandatory J		Ŵ	Stebility	Unstable	Conditions to Avera		
CFR 1910.1200. Standard must be should for specific regularments.	Form Approved			·	Stable	<u> </u>		
ENTITY (As Used on Labor and Latt)	OMB No. 1218-00	372 and not permitted. If any item 4s not a				X		·····
Slaslonomer Type It Liquid	alomation is a	averiable, the space must be marked	to vidicate that,		(Materials to Avold	N/A		·
estion 1		, 		Hazardous Deci	mposition or Bypro	ducts N/A		
andactorer's Name Shofu Dental Corporation	Emergency Telephor 1-800-535-505	ne Number		Hazardous Polymerizetion	Мау Оссол	Conditions to Avoid	}	
ddress (Number, Street, City, State, and Z/P Dode) 225 Stone Drive	Telephone Number 760-736-3277				Will Not Occur	x		
San Marcos, CA 92078	Data Prepared	CTOBER 1, 2002	······		- Health, Hazar			
	Signature of Prepare			Picute(s) of Entr		halation? N/A	Skint Possible	Passible
	<u> </u>	- <u></u>		Health Herends	(Acute and Chronic	Avoid skin and	eye contact. Could c	auge irritation.
iection II — Hazardous Ingredients/Identi	ty information	Other Lantis						
azardous Components (Specific Chemical Identity: Co	mmon Name(s)) OSHA FEL	ACGIH TLV Recommanded	i 96 poprionei)		·····	· · · · · · · · · · · · · · · · · · ·	<u> </u>	
				Cardnogenicity	N	ITP? N/A	MRC Monographs? N	/A OSHA Regulated?
·			<u> </u>					
			m	Signs and Sym	ptome of Exposure	Skin or eye irr	Instion	
No hazardous material present in	expensive for experter t	han 17 (D 17 For caret	(nodens)	•				
TO MAZALOODA NALEY UNI PLEBENT 21	CODUCTIVITATION GLEATEL .		inogena/1	Medical Consil	ons wated by Exposure		······	
	·			C Benerally Aggs	avated by Exposure	Unknown		·····
······	······································			Emergency an	First Aid Procedure	153		necessary. Skin contact: V
·								
								. Contact physician if necsr
						s for Safe Handling and at is Released or Spilled	d U10	······································
Section III - Physical/Chemical Characte	riatics			Hipe up	and discard	in a suitable con	tainer	
Boiling Post	N/A Specific Gravity (H2	0 - 1) Above 1.0	1					
Vapor Pressure (mm Hg.)	Melling Print			Waste Olapoar	Method			
Vapor Densily (AIR - 1)	N/A Eveporation Rate		- <u>Ν/λ</u>	· · · ·			state, and local regu	lations
	N/A (Sutyl Acetait - 1)		N/A	Precausions to	Be Taken in Hand	ing and Storing		
Solubility in Water Complete				Store II		with lid tightly c	Insed	
Appearance and Odor	······································			Other Precaut		aten yra ergning e		
	esa, viscous liquid							ording to instructions for u
Section IV Fire and Explosion Hazard Past Point (Method Used)			1				miar ebactariara acco	Matif to Instructiona rol o
N/A	Flammable Limits	N/A LEL	UEL.		i Control Mi stection (Specify Ty			
Extinguishing Madia N/A		······································		Veniliation		<u> </u>		
Special Fire Fighting Procedures				Venliietton	Local Exheust		Special	
N/A			······	N/A	Mechanical (Ge	nensij	Othur	
				Protective Glo	ves N/A		Eye Protection	Hay be required
Unusual Fire and Explosion Hazards N/A		<u></u>		Other Protect	ve Clothing or Equi	pment		lay be required
				Work/Hygiana	Practices	N/A		
						N/A		
Reproduce locally)		05	SHA 174, Sept. 1985				Page 2	● URGPO 1848_491-529.
		I PRODUCTION AND AND AND AND AND AND AND AND AND AN		in and the second	ana ing Ani	kila durta	en de la composition de la composition	n galantin nan an a



	r mining date. August 20, 2013		
SCTIO	N 1. Identification of the substance or mixture and of the supplier		
1.1	Product identifier		
	Trade Name:		
	Glaslonomer Cement Type II "LIQUID"		
1.2	Relevant identified uses of the substance or mixture and uses advised against		
1.2	Relevant identified uses: Dental material		
	Uses advised against: No further data		
1.3	Details of the supplier of the safety date sheet		
	Company/Undertaking identification		
	Manufacturer's Name: SHOFU DENTAL CORPORATION		
	Address: 1225 Stone Drive, San Marcos, CA 92078 USA		
	Toll Free: 1-800-827-4638		
	Phone: 760-736-3277		
	Fax: 760-736-3276		
	E-Mail: customer-service@shofu.com		
	Section in Charge: Quality Management & Regulatory Affairs		
1.4	Emergency Telephone Number		
	For emergencies only. Call CHEMTREC: +1 703-741-5970 / 1-800-424-9300 (24 hours)		
SCTIO	N 2. Hazards identification		
2.1	GHS Classification		
	PHYSICAL HAZARDS		
	FLAMMABLE LIQUIDS Not Classified		
	The thing without mention is out of a classification object. Or cannot classify it.		
2.2	Label elements		
2.2			
	SYMBOL Void		
	SIGNAL WORD Void		
	HAZARD STATEMENTS Void		
	PRECAUTIONARY STATEMENTS		
	[Prevention]		
	Obtain special instruction before use.		
	Do not handle until all safety precautions have been read and understood.		
	[Response]		
	Get medical advice/attention if you feel unwell.		
	[Storage]		
	Store in a cool and dark area.		
	[Disposal]		
	Dispose of contents and container in accordance with regulation.		
2.3	Other hazards		
	Results of PBT and vPvB assessment		
	PBT: Not applicable.		



·	Printing date: August 26, 2019
	vPvB: Not applicable.
SCTIO	N 3. Composition/information on ingredients
3.1	Chemical characterization: Mixtures
3.2	Description: -
3.3	Dangerous components: Void
	Copolymer of acrylic acid and tricarboxylic acid (Water solution) 90-99 %
	Tartaric acid [Cas No.87-69-4] 1-10 %
	Others
3.4	Additional information: For the wording of the listed risk phrases refer to section 2
	5
SCTIO	N 4. First-aid measures
4.1	Description of first aid measures
	Eye contact: Rinse cautiously with water for several minutes. Remove contact lenses, if present
	and easy to do. If eye irritation persists, get medical advice/attention.
	Skin contact: Wash immediately with soap and plenty of water. If on skin, skin irritation, get
	medical advice/attention.
	Ingestion: Rinse mouth and seek medical advice if necessary.
	Inhalation: Remove victim to fresh air and keep at rest in a position comfortable for breathing
	If symptom concerning breath goes out, call a POISON CENTER or doctor.
4.2	Most important symptoms and effects, both acute and delayed
4.2	
10	No further relevant information available.
4.3	Indication of any immediate medical attention and special treatment needed
	No further relevant information available.
COTIO	
SCTIO	
5.1	Extinguishing Media:
	Foam, CO ₂ , Powder, Dry sand
5.2	Special hazards arising from the substance or mixture:
	No further relevant information available.
5.3	Advice for firefighters:
	No special measures required.
SCTIO	
6.1	Personal precautions, protective equipment and emergency procedures:
_	Avoid contact with eyes and skin.
6.2	Environmental Precautions:
	Send to approved treatment/disposal company or dispose according to local, state and
	federal regulations.
6.3	Methods and material for containment and cleaning Up:
	Wipe up and discard in a suitable container.
6.4	Reference to other section:
	See Section 7 for information on safe handling.
	See Section 8 for information on personal protection equipment.
	See Section 13 for disposal information.
	Version Number 7



SCTION 7. Handling and storage 7.1 Precautions for safe handling: Avoid inhaling and contact with eyes and skin. Keep away from ignition sources and separate from strong oxidizer. 7.2 Conditions for safe storage, including any incompatibilities: Store in a cool and dry place out of direct sunlight and source of ignition. Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Pust mask Skin Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following					
Avoid inhaling and contact with eyes and skin. Keep away from ignition sources and separate from strong oxidizer. 7.2 Conditions for safe storage, including any incompatibilities: Store in a cool and dry place out of direct sunlight and source of ignition. Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be acclusted in advance and has to be checked prior to the application. <th>SCTIO</th> <th>N 7. Handling ar</th> <th>nd storage</th>	SCTIO	N 7. Handling ar	nd storage		
Keep away from ignition sources and separate from strong oxidizer. 7.2 Conditions for safe storage, including any incompatibilities: Store in a cool and dry place out of direct sunlight and source of ignition. Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Usus mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the available gloves does not only depend on the material, but also on turther marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of t	7.1	Precautions for saf	e handling:		
Keep away from ignition sources and separate from strong oxidizer. 7.2 Conditions for safe storage, including any incompatibilities: Store in a cool and dry place out of direct sunlight and source of ignition. Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Usus mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the available gloves does not only depend on the material, but also on turther marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of t		Avoid inhaling and contact with eyes and skin.			
 7.2 Conditions for safe storage, including any incompatibilities: Store in a cool and dry place out of direct sunlight and source of ignition. Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product the preparation/the chemical mixture. Selection of the gloves The selection of the gloves material on consideration of the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the application. Penetration time of glove material and values and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the maturfacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butly rubber, NBR Eye Protection: Safety goggles Stroen S. Physical and chemical properties Appearance//doc//Colour: Odourless, color less liquid Odour threshold Not determined. 					
Store in a cool and dry place out of direct sunlight and source of ignition. Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Uust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the gloves material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance//dor/Colour: Odourless, color less liquid Odour threshold Not determined.	72				
Separated from organic peroxide. Keep containers closed. 7.3 Specific end use(s): No further relevant information available. SCTION 5. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product the preparation/the chemical mixture. Selection of the gloves material on consideration of the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the substance, the resistant coll is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the premarent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold Not determined.	1.2				
 7.3 Specific end use(s): No further relevant information available. SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer to the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined. 					
SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the glove material on consideration of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Material of gloves The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Appearance/Odor/Colour: Odourthess,		-			
SCTION 8. Exposure controls/personal protection 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the gloves material of gloves The selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR </th <th>7.3</th> <th>Specific end use(s)</th> <th>:</th>	7.3	Specific end use(s)	:		
 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colou: Odourless, color less liquid Odour threshold Not determined. 		No further re	evant information available.		
 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colou: Odourless, color less liquid Odour threshold Not determined. 					
 8.1 Control parameters: Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined. 	SCTIO	N 8. Exposure c	ontrols/personal protection		
Ingredients with limit values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation. Due to missing tests no recommendation to the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrie rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold Not determined.					
The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Appearance/Odor/Colour: Odour less, color less liquid Odour threshold Not determined.	0.1	•			
have to be monitored at the workplace. 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the gloves material on consideration of the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold Not determined.		•			
 8.2 Exposure controls: Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined. 		•			
Respiratory Protection: Dust mask Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.			e monitored at the workplace.		
Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colur: 9.1 Information on basic physical and chemical properties Appearance/Odor/Colur: Appearance/Odor/Colur: Odourless, color less liquid Not determined.	8.2	Exposure controls:			
Skin Protection: Hand Protection The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold Odourless, color less liquid		Respiratory Protect	tion:		
The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles Setty orggles 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined. Not determined.			Dust mask		
 substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles 		Skin Protection:	Hand Protection		
substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Mitrile rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles Settor on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Not determined.			The glove material has to be impermeable and resistant to the product/ the		
Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
for the product/ the preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation. • Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Not determined. Not determined.					
rates of diffusion and the degradation. Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
 Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable:			-		
The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. • Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. • For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odour threshold			rates of diffusion and the degradation.		
the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Not determined. 			· Material of gloves		
the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Not determined. 			The selection of the suitable gloves does not only depend on		
SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold Not determined.			5 7		
of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
Prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odour threshold Not determined. 			-		
 Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined. 			not be calculated in advance and has therefore to be checked		
The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.			prior to the application.		
manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.			Penetration time of glove material		
manufacturer of the protective gloves and has to be observed. For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.			The exact break through time has to be found out by the		
 For the permanent contact of a maximum of 15 minutes gloves made of the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined. 					
the following materials are suitable: Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
Butyl rubber, BR Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
Nitrile rubber, NBR Eye Protection: Safety goggles SCTION 9. Physical and chemical properties 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.			5		
Eye Protection: Safety goggles SCTION 9. Physical and chemical properties 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
SCTION 9. Physical and chemical properties 9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.			Nitrile rubber, NBR		
9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.		Eye Protection:	Safety goggles		
9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.					
9.1 Information on basic physical and chemical properties Appearance/Odor/Colour: Odourless, color less liquid Odour threshold Not determined.	SCTIO	N 9. Physical an	d chemical properties		
Appearance/Odor/Colour:Odourless, color less liquidOdour thresholdNot determined.					
Odour threshold Not determined.					
			·		
pH Not determined.		рН	Not determined.		



SAFETY DATA SHEET

	Melting point/freezing point	Not determined.
	Boiling Point:	≈ 100 °C
	Flash point:	Not determined.
	Evaporation rate	Not determined.
	Flammability (solid, gas)	Not applicable.
	Upper/lower flammability or explosive limits	Not determined.
	Vapour pressure	Not determined.
	Vapour density	Not determined.
	Relative Density:	1.27 (water=1)
	Solubility: water solubility	Soluble.
	Partition coefficient: n-octanol/water	Not determined.
	Auto-ignition temperature	Not determined.
	Decomposition temperature	Not determined.
	Viscosity	Not determined.
	Explosive properties	Not applicable.
	Oxidising properties	Not applicable.
9.2	Other information	

No further relevant information available.

SCTION 10. Stability and reactivity

10.1 Reactivity:

No further relevant information available.

- 10.2 Chemical stability:
 - Stable under normal temperatures and pressures.
- 10.3 Possibility of hazardous reactions:

No dangerous reactions known.

10.4 Condition to Avoid:

Avoid direct sunlight and high temperature.

10.5 Incompatible materials:

No further relevant information available.

10.6 Hazardous Decomposition Products:

None under normal conditions of storage and use.

SCTION 11. Toxicological information

11.1 Information on toxicological effects: Acute toxicity: Based on available data, the classification criteria are not met. Skin corrosion/irritation: Based on available data, the classification criteria are not met. Eye damage/irritation: Based on available data, the classification criteria are not met. Sensitization to the respiratory tract: Based on available data, the classification criteria are not met. Skin sensitization: Based on available data, the classification criteria are not met. Germ cell mutagenicity/Genotoxicity: Based on available data, the classification criteria are not met. Carcinogenicity: Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Reproductive toxicity: Effects on or via lactation: Lack of data.



SAFETY DATA SHEET

		Printing date: August 26, 2019
	Specific target organ toxi	city (single exposure):
		Based on available data, the classification criteria are not met.
	Specific target organ toxi	city (repeated exposure):
		Based on available data, the classification criteria are not met.
	Aspiration hazard:	Based on available data, the classification criteria are not met.
SCTIO	N 12. Ecological inform	ation
	Toxicity:	
12.1	•	information available.
12.2	Persistence and degrada	
12.2	-	information available.
12.2		
12.3	Bioaccumulative potentia	
		information available.
12.4	Mobility in soil:	
		information available.
12.5	Results of PBT and vPvB	assessment:
	Not applicable.	
12.6	6 Other adverse effects:	
	No further relevant	information available.
SCTIO	N 13. Disposal conside	rations
13.1	Waste treatment methods	S:
	Dispose of contents/conta	ainer to in accordance with local/regional/national/international
	regulations.	
SCTIO	N 14. Transport information	ation
14.1	UN number:	Void
14.2	2 UN proper shipping name	e: Void
	B Transport hazard class(e	
	Packing group:	Void
	Environmental hazards:	No
	Special precautions for us	
		ng to Annex II of MARPOL73/78 and the IBC Code:
''		Not applicable.
SCTIO	N 15 Degulatery inform	noti
30110		
	Follow all regulations in y	our country.
SCTIO		
	I his product is intended f	or use by dental professionals. (instrument/material)
	Abbreviations and acrony	ms:
	CAS: Chemical	Abstracts Service (division of the American Chemical Society)
	PBT: Persistent,	Bioaccumulative and Toxic
		Bioaccumulative and Toxic istent and very Bioaccumulative